

GLAZE

APPLICATIONS Hospitality, Contract, Automotive & RV, Residential

GENERAL SPECIFICATIONS

Width 54"
Roll Size 30 Yards
Thickness 1.1 mm
Weight 36 Ounces per Linear Yard
Backing Polyester / Cotton

PERFORMANCE SPECIFICATIONS

Abrasion Resistance 100,000+ Double Rubs ASTM D 4157-10 Wyzenbeek / CFFA-1A
Ultra Violet Resistance 200 Hours ASTM G26-96 Method C / CFFA-2
Cold Crack -10° F Federal Standard No. 191A-Method 5874 / CFFA-6

FLAMMABILITY REQUIREMENTS *

California Fire Code Technical Bulletin No. 117, Section E
BIFMA
UFAC Class 1
MVSS 302
NFPA 260
IMO A.652 (16) 8.2
IMO A.652 (16) 8.3
ASTM E84: Class I or A Rating
May Comply with California 133 when Tested with Suitable Components

CLEANING INSTRUCTIONS

Prompt cleaning is always recommended. Ordinary dirt and stains can be removed with a mild soap and water. Rinse the cleaned area with clean water and dry with a lint-free cloth. Glaze will resist, without serious discoloration, the repeated actions of normal dilutions of non-abrasive chlorine or ammonia-based cleaners.



202 SOUTH 12th ST.
BIRMINGHAM, ALABAMA 35233
LOCAL PHONE 205-322-3476 • WATS LINE 800-326-2726
FAX 205-322-3484
email: mascofabrics@aol.com
www.mascofabrics.com

* This term and any corresponding data refer to typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions. 2.12